# Effect of Water Absorption and Sorptivity on Durability of Pozzocrete Mortar

## Rushabh A. Shah, Jayeshkumar Pitroda

Abstract- After evaporation of excess water in the mortar, voids inside the mortar creates capillaries which are directly related to porosity and permeability of the mortar. Proper selection of ingredients, adequate mix proportioning & followed by good construction practices lead to almost impervious mortar. Due to incomplete compaction; mortar may consists gel pores & capillary pores, which leads to low strength of mortar. Due to problems associated with the absorption test and permeability test; which are measuring the response of mortar to pressure which is rarely the driving force of fluids entering in to mortar; hence there is a need for another type of test. Such tests should measure the rate of absorption of water by capillary suction; "sorptivity" of unsaturated mortar. In this paper, an attempt is made to study sorptivity and water absorption properties of Pozzocrete mortar. The mix design was carried out for 1:3 proportion cement mortar on the basis of IS 269:1970.

Key words-capillary suction, sorptivity, water absorption, Pozzocrete, mortar

## I. INTRODUCTION

Mortar is a material having tiny spaces through which liquid or air may pass. The durability of mortar depends largely on the movement of water and gas enters and moves through it. The permeability is an indicator of mortar's ability to transport water more precisely with both mechanism that is controlling the uptake and transport of water and gaseous substances into cementitious material. whileSorptivity is materials ability to absorb and transmit water through it by capillary suction.

Uptake of water by unsaturated, hardened mortar may be characterized by the sorptivity. This is a simple parameter to determine and is increasingly being used as a measure of mortar resistance to exposure in aggressive environments.

Sorptivity, or capillary suction, is the transport of liquids in porous solids due to surface tension acting in capillaries. It is a function of the viscosity, density and surface tension of the liquid and also the pore structure (radius, tortuosity and continuity of capillaries) of the porous solid. It is measured as the rate of uptake of water. Transport mechanisms act at the level of the capillary pores and depend on the fluid and the solid characteristics. The porous structure of mortar is intimately related with its permeability. A low water/cement ratio results in mortar structures which are less permeable because they are characterized by having small pores which are not interconnected.

 TABLE 1

 ACCEPTANCE LIMITS FOR DURABILITY INDEXES

Accepta	nce Criteria	OPI (log scale)	Sorptivity (mm/h)
Laboratory 1	mortar	>10	< 6
As-built	Full	> 9,4	< 9
Structures	acceptance		
	Conditional	9,0 to 9,4	9 to 12
	acceptance		
	Remedial	8,75 to 9,0	12 to 15
	measures		
	Rejection	< 8,75	>15

# **II. DESIGN MIX MATERIALS**

#### a) Supplementary cementitious material: Pozzocrete Pozzocrete (P40, P60 and P100)

Pozzocrete (P40, P60 and P100) is a high efficiency pozzolanic material, obtained by selection, processing and testing of fly ash resulting from the combustion of coal at electricity generating power stations. It is subjected to strict quality control procedures. P60 confirms to IS: 3812 part-1 fly ash and P40 confirms to ASTM 618 fly ash for use as component of cement with Portland clinker.

TABLE-2

GENERAL PROPERTIES OF POZZOCRETE						
Property	P40	P60	P100			
Presentation	Finely	Finely	Finely			
	divided dry	divided dry	divided			
	powder	powder	dry			
			powder			
Specific	2.3	2.3	2.3			
Gravity						
Colour	Light grey	Light grey	Greyish			
			white			
Bulk weight	1.0 tonne per	1.0 tonne	0.65 tonne			
(tonne per	m <sup>3</sup>	per m <sup>3</sup>	per m <sup>3</sup>			
m <sup>3</sup> )						
Loss on	<2.5%	<2.5%	<2.5%			
Ignition						

#### Manuscript received on March, 2013

Rushabh A. Shah, Student of final year M.E. C E & M,B.V.M. Engineering College, Vallabh Vidyanagar

Jayeshkumar Pitroda, Assistant Professor & Research Scholar, Civil Engg Department, B.V.M. Engg.College, Vallabh Vidhyanagar-Gujarat-India



Published By: Blue Eyes Intelligence Engineering & Sciences Publication

Particle size	<25%	<18%	Zero
	retained on	retained on	retention
	45 micron	45 micron	on 45
	sieve	sieve	micron
			sieve, less
			than
			0.25%
			retained on
			25 micron
			sieve
Particle	Spherical	Spherical	Spherical
shape			_
Package	1 tonne	30 kg bags,	30 kg bags
-	big-bags and	1 tonne	
	bulk tankers	big-bags	
		and bulk	
		tankers	

#### **b**) Cement

The cement used is SANGHI OPC 53 grade cement. The Ordinary Portland Cement of 53 grade conforming to IS: 8112-1989is be use. Tests were conducted on cement like Specific gravity, consistency tests, setting tests, soundness, Compressive strength N/mm<sup>2</sup> at 28 days.



Fig 1: SANGHI CEMENT

TABLE -3 **PROPERTIES OF CEMENT** 

Sr.no.	properties	Result	Requirements as per IS:8112-1989
1	Specific gravity	3.15	3.10-3.15
2	Standard consistency (%)	31.5 %	30-35
3	Initial setting time (hours, min)	91 min	30 minimum
4	Final setting time (hours, min)	211 min	600 maximum
5	Compressive strength	58 N/mm <sup>2</sup>	53 N/mm <sup>2</sup> minimum

#### d) Fine aggregate

Those fractions from 4.75 mm to 150 micron are termed as fine aggregate. The river sand is used as fine aggregate conforming to the requirements of IS: 383. The river sand is washed and screened, to eliminate deleterious materials and over size particles.



Fig 2: Fine aggregate (River sand)

#### TABLE-4 PROPERTIES OF SAND

Property	Fine Aggregate (River sand)
Fineness modulus	3.1
Specific Gravity	2.767
Water absorption (%)	1.2
Bulk Density (gm/cc)	1.78

## e) Water

Water is an important ingredient of Mortar as it actually participates in the chemical reaction with cement. Since it helps to from the strength giving cement gel, the quantity and quality of water is required to be looked into very carefully.

# **III.DESIGN MIX METHODOLOGY**

## a) Design Mix

A cement mortar mix 1:3 was designed as per IS: 269 methods and the same were used to prepare the test samples. The design mix proportion is done in Table 5,6 and 7.

TABLE - 5				
MIX DESIGN PROPORTIONS				
	<b>TT</b> 7 - 4	<b>C</b>	<b>T</b> *	

	Water	Cement	Fine aggregate
By Weight, [gms]	86	200	600
By Volume, [m <sup>3</sup> ]	0.43	1	3

#### TABLE-6 **CEMENT REPLACEMENT BY POZZOCRETE (P40, P60** AND P100)

Sr. No.	Types of	<b>Description of Mortar</b>
	Mortar	
1	A1	River Sand Mortar (1:3)
2	B1	10% Cement Replacement by
		Pozzocrete (P40)
3	B2	30% Cement Replacement by
		Pozzocrete (P40)
4	B3	50% Cement Replacement by
		Pozzocrete (P40)
5	C1	10% Cement Replacement by
		Pozzocrete (P60)
6	C2	30% Cement Replacement by
		Pozzocrete (P60)
7	C3	50% Cement Replacement by
		Pozzocrete (P60)



Published By:

& Sciences Publication

International Journal of Emerging Science and Engineering (IJESE) ISSN: 2319–6378, Volume-1 Issue-5, March 2013

0	D1	100/ C (D 1 )
8	DI	10% Cement Replacement by
		Pozzocrete (P100)
9	D2	30% Cement Replacement by
		Pozzocrete (P100)
10	D3	50% Cement Replacement by
		Pozzocrete (P100)

TABLE- 7 MIX PROPORTION FOR MORTAR

		Design Mix Proportions For Mortar (1:3)				
M.T.	W/C ratio	С	F.A.	P 40	P 60	P 100
A1	0.45	1	3	-	-	-
B1	0.45	0.9	3	0.1	-	-
B2	0.45	0.7	3	0.3	-	-
B3	0.45	0.5	3	0.5	-	-
C1	0.45	0.9	3	-	0.1	-
C2	0.45	0.7	3	-	0.3	-
C3	0.45	0.5	3	-	0.5	-
D1	0.45	0.9	3	-	-	0.1
D2	0.45	0.7	3	-	-	0.3
D3	0.45	0.5	3	-	-	0.5
C2 C3 D1 D2 D3	0.45 0.45 0.45 0.45 0.45	0.7 0.5 0.9 0.7 0.5 W/C	3 3 3 3 3 3	- - - - -	0.3 0.5 -	- 0.1 0.3 0.5

M.T. =Mortar Type, W/C ratio= Water/Cement Ratio,C= Cement, F.A. = Fine Aggregate,

## b) Water absorption test

The 70.7 mm x 70.7 mm x 70.7mm size cubeafter casting were immersed in water for 28 days curing. These specimens were then oven dried for 24 hours at the temperature85°C until the mass became constant and again weighed. This weightwas noted as the dry weight (W1) of the cylinder. After that the specimen was kept in water at 85°c for 24 hours. Then this weight was noted as the wet weight (W2) of the cylinder.

% water absorption = [(W2–W1) / W1] x 100 Where, W1 = Oven dry weight of cubes in grams

W2 = After 24 hours wetweight f cubes in grams.



Fig 3: Setup of Oven



Fig 4: Setup of Hot Water Curing

## c) Sorptivity test

The sorptivity can be determined by the measurement of the capillary rise absorption rate on reasonably homogeneous material. Water was used of the test fluid. The cubes after casting were immersed in water for 28 days curing. The specimen size 70.7 mm x 70.7 mm x 70.7 mm after drying in oven at temperature of 85 °C were drowned as shown in figure 6 with water level not more than 5 mm above the base of specimen and the flow from the peripheral surface is prevented by sealing it properly with non-absorbent coating. The quantity of water absorbed in time period of 30 minutes was measured by weighting the specimen on a top pan balance weighting upto 0.1 mg. surface water on the specimen was wiped off with a dampened tissue and each weighting operation was completed within 30 seconds.

Sorptivity (S) is a material property which characterizes the tendency of a porous material to absorb and transmit water by capillarity. The cumulative water absorption (per unit area of the inflow surface) increases as the square root of elapsed time (t)

I=S.t<sup>1/2</sup> therefore S=I/t<sup>1/2</sup> Where; S= sorptivity in mm, t= elapsed time in mint.

## $I=\!\Delta w\!/Ad$

 $\Delta w$ = change in weight = W2-W1

W1 = Oven dry weight of cylinder in grams

W2 = Weight of cylinder after 30 minutes capillary suction of water in grams.

A= surface area of the specimen through which water penetrated.

d= density of water



Fig 5: Setup of weight

Published By: Blue Eyes Intelligence Engineering & Sciences Publication





Fig 6: Setup of Sorptivity

## **IV.EXPERIMENTAL RESULTS**

Table-8 and 9 gives the water absorption and Sorptivity test results of % replacement of fly ash in mortar for 28 days curing. The % replacement vs % water absorption and Sorptivity results are graphically shown in figure 7 and 8.

**TABLE 8 AVERAGE % WATER ABSORPTION AT 28 DAYS** 

Mortar Type	DryWt in grams (W1)	Wet Wt in grams (W2)	% Water Absorption
A1	772	806	2.77
B1	776	806	3.08
B2	780	804	3.84
B3	769	804	4.83
C1	770	798	3.67
C2	788	818	3.75
C3	752	781	3.85
D1	780	812	2.90
D2	801	825	3.00
D3	783	806	4.14



Fig. 7: % Replacement of cement versus % water absorption 

IADLE- 9				
SORPTIVITY AT 28 D	AYS			

Mortar Type	Dry Wt in grams (W1)	WetWt in grams (W2)	Sorptivity value in 10 <sup>-4</sup> mm/min <sup>0.5</sup>
A1	793	797	1.46
B1	797	800	1.10
B2	800	802	0.73
B3	797	800	1.10
C1	790	792	0.73

C2	810	813	1.10
C3	772	775	1.10
D1	802	804	0.73
D2	818	822	1.46
D3	799	802	1.10



Fig. 8: % Replacement of cement versus sorptivity

## **V. CONCLUSION**

Based on limited experimental investigation concerning the water absorption and sorptivity of mortar, the following observations are made regarding the resistance of partially replaced Pozzocrete1:3 proportion mortar:

- (a) The water absorption of Pozzocrete P40, P60and P100 in Pozzocrete 1:3 mortar mix higher than traditional mortar.
- (b) Where percentage increase in water absorption is found to be 4.83% for P40, 3.85% for P60, 4.14% for P100 and sorptivity is found to be 1.10 mm/min<sup>0.5</sup> for P40, 1.10 mm/min<sup>0.5</sup> for P60, 1.10 mm/min<sup>0.5</sup> for P100 respect to reference mix.
- (c) The water absorption and sorptivity of P40,P60 and P100 Pozzocrete1:3 proportion mortar shows higher water absorption and lesser sorptivity than traditional mortar.
- The Pozzocrete can be innovative supplementary (d) cementitious Construction Material but judicious decisions are to be taken by engineers.

## ACKNOWLEDGEMENT

The Authors thankfully acknowledge to Dr.C.L.Patel, Chairman, Charutar Vidya Mandal, Er.V.M.Patel, Hon.Jt. Secretary, Charutar Vidya Mandal, Mr. Yatinbhai Desai, Jay Maharaj construction, Vallabh Vidyanagar, Gujarat, India for their motivational and infrastructural support to carry out this research.

## REFERENCES

- 1. Atis, C. D. (2003). "Accelerated carbonation and testing of mortar made with fly ash." Construction and Building Materials, Vol. 17, No. 3, pp. 147-152.
- 2. Bai j., Wild S, Sabir BB (2002) "Sorptivity and strength of air-cured and water cured PC-PFA-MK mortar and the influence of binder composition and carbonation depth". Cement and mortar research 32:1813-1821.
- 3. Bentz, D., Ehlen, M., Ferraris, C., and Garboczi, E. "Sorptivity-Based Service Life Predictions for Mortar Pavements." 181-193.
- 4. Caliskan, S. (2006). "Influence of curing conditions on the sorptivity and weight change characteristics of

self-compacting mortar." The Arabian Journal for Science and Engineering, 31(1), 169-178.

Published By:

& Sciences Publication



## International Journal of Emerging Science and Engineering (IJESE) ISSN: 2319-6378, Volume-1 Issue-5, March 2013

- Claisse, P. A. (1997). "Absorption and Sorptivity of Cover 5. Mortar." Journal of Materials in Civil Engineering, 9(3), 105-110.
- Dias, W. P. S. (2000). "Reduction of mortar sorptivity with age 6. through carbonation." Cement and Mortar Research, 30(8), 1255-1261.
- Deepa A Sinha, Dr.A.K.Verma, Dr.K.B.Prakash (2012) "Sorptivity 7. and waste absorption of steel fibers reinforced ternary blended mortar". International journal: global research analysis (GRA),volume:1,issue:5,oct2012,issn no:2277-8160.
- Gonen, T. and Yazicioglu, S. (2007). "The influence of 8. compactionpores on sorptivity and carbonation of mortar." Construction and Building Materials, Vol. 21, No. 5, pp. 1040-1045.
- Güneyisi, E. and Gesog'lu, M., (2008). "A study on durability 9. properties of high-performance mortars incorporating high replacement levelsof slag." Materials and Structures, Vol. 41, No. 3, pp. 479-493.
- Hall, C. (1977). "Water movement in porous building 10. materials -- I. Unsaturated flow theory and its applications." Building and Environment, 12(2), 117-125.
- 11. Hall, Christopher; Hoff, William D (2012). Water transport in brick, stone and mortar, 2nd edn. London and New York: Taylor and Francis. http://www.routledge.com/books/details/9780415564670/.
- Jayeshkumar Pitroda, Dr. F S Umrigar (2013), "Evaluation of 12. Sorptivity and Water Absorption of Concrete with Partial Replacement of Cement by Thermal Industry Waste (Fly Ash) "International Journal of Engineering and Innovative Technology (IJEIT) Volume 2, Issue 7, January 2013, ISSN: 2277-3754, ISO 9001:2008 Certified, pp-245-249.
- Prof. Jayeshkumar Pitroda, Dr. L.B.Zala, Dr.F.S.Umrigar (2013), 13. "Durability of concrete with Partial Replacement of Cement by Paper Industry Waste (Hypo Sludge)"International Journal of Innovative Technology and Exploring Engineering (IJITEE), ISSN: 2278-3075, Volume-2, Issue-3, February 2013 / 101-104
- Philip, John R (1957). "The theory of infiltration: 4. Sorptivity and 14 algebraic infiltration equations". Soil Science 84: 257-264.
- Rushabh A. Shah, Prof. Jayeshkumar Pitroda (2013), "Effect of Pozzocrete as Partial Replacement with Cement in Mortar" 15. International Journal Global Research Analysis, (GRA), Volume: 2, Issue: 1, Jan 2013, ISSN No 2277 - 8160, pp-44-46.
- Rushabh A. Shah, Prof. Jayeshkumar Pitroda (2013), "Pozzocrete: 16. Partially with Modern Material Replaced Cement in Mortar "International Journal of Innovative Technology and Exploring Engineering (IJITEE), ISSN: 2278-3075, Volume-2, Issue-3, February 2013 / 105-108
- Rushabh A. Shah, Prof. Jayeshkumar Pitroda (2013), "Fly Ash Class F: 17 Opportunities for Development of Low Cost Mortar"International Journal of Innovative Technology and Exploring Engineering (IJITEE), ISSN: 2278-3075, Volume-2, Issue-4, February 2013 / 112-115
- 18. Sulapha, P., Wong, S. F., and Wee, T. H., and Swaddiwudhipong, "Carbonation of mortar containing S.(2003). mineral admixtures." Journal of Materials in Civil Engineering, Vol. 15, No. 2, pp. 134-143.
- 19. Song X.J, Marosszeky M, Brungs M, Munn R. 2005. Durability of fly ash based Geopolymer mortar against sulphuric acid attack 10 DBMC International Conference on Durability of Building Materials and Components, Lyon, France, 17-20 April.

## **AUTHORS PRORIFLE**



RushabhAjaykumar Shah , was born in 1990 in Vyara Town. He received his Bachelor of Engineering degree in Civil Engineering from the Birla Vishvakarma Mahavidyalaya Engineering Collage, Sardar Patel University, Vallabh Vidya Nagar in 2011. At present he is Final year student of Master's Degree in Construction Engineering and Management from Birla Vishvakarma Mahavidyalaya, Gujarat Technological University.He has papers published in International Journals.



Prof. Jayeshkumar R. Pitroda, was born in 1977 in Vadodara City. He received his Bachelor of Engineering degree in Civil Engineering from the Birla Vishvakarma Mahavidyalaya, Sardar Patel University in 2000. In 2009 he received his Master's Degree in Construction Engineering and Vishvakarma Management from Birla Mahavidyalaya, Sardar Patel University. He

joined Birla Vishvakarma Mahavidyalaya Engineering College as a faculty where he is Assistant Professor of Civil Engineering Department with a total experience of 12 years in field of Research, Designing and education. He has papers published in National Conferences and International Journals.



Published By:

& Sciences Publication